


# Vario Solid Lasur

- Vario Solid Glaze -  
**Exterior and interior**  
**High Solid Middle-Layer Glaze, silk gloss**

---

## General Description

Type of material:	High-quality solvent-containing middle-layer glaze based on an innovative alkyd resin/oil combination
Range of uses:	Prime and top coat for all wooden elements (wooden houses, pergolas, boardings, fences, windows and external doors).
Product properties:	Extremely high penetration due to the employment of special oils. Optimal long-term protection due to high solids content. Non-drip with good edge protection, easy to apply, free of biocides, optimal protection against UV-rays.
Colour shades:	Colourless (*), Old pine, Pine, Ash, Light oak, Teak, Mahogany, Dark oak, Walnut, Rosewood, White *Due to the missing colour pigments, <b>Jansen Vario Solid Glaze colourless</b> should only be applied outdoors in conjunction with a coloured glaze, otherwise no UV protection is possible.
	 <b>MIX</b>
Packaging sizes:	750 ml, 2,5 l, 5 l

---

## Technical Data

Binder base:	alkyd resin/oil combination
Pigment base:	micronized iron oxide, titanium dioxide
Density:	ca. 0,910 – 0,950 g/cm <sup>3</sup> depending on shade
Degree of gloss:	silk-gloss
Viscosity:	slightly thixotropic
Thinner:	apply without diluting

Drying	(23 °C 60 % rel. air humidity) dust-dry: after 4- 6 hours re-coatable: after overnight drying
Spreading rate:	10 – 15 m <sup>2</sup> / l per coat, depending on the absorbency of the substrate
GISCODE:	BSL10

---

**Method of processing**

Substrate preparation:	<p>The substrate must be portative, dry, clean and free of separating substances (oil, grease, wax). The wood moisture may reach a max. of 18 %, dimensionally stable wooden structures max. 15%. In the case of exterior rough woods highly endangered by blue stain, where necessary prime with Jansen Wood Primer (please observe the technical data sheet and BFS No. 18 table in section 2.1.4). Pay attention to constructive wood protection (curved edges, angle of run-off etc.). Intact old coatings are to be carefully sanded. Old coatings which do not adhere well are to be completely removed and then to be treated as rough wood.</p> <p>The preparation of the substrate and painting must be scientifically and technically state of the art. Please also take note of the current BFS data sheets and the VOB (German Construction Contract Procedures), Part C, DIN 18363 Painting and Coating work.</p>
Application:	<p>Jansen Vario Solid Glaze is supplied ready for use. On dimensionally unstable wooden elements (e.g. wooden fences) 1-2 coats, on elements which are dimensionally stable or of limited stability 2 coats. The colour score is influenced by various types of wood as well as through the layer thickness. The shades can be mixed together. A lightening can be effected with colourless.</p> <p>When applying on tropical woods, please observe the appropriate technical data sheet. As an exterior application, ash does not maintain a weatherproof coating.</p> <p><b>Before processing, carry out trial coating.</b></p> <p><b>If several containers are used to apply the final coat, ensure batch uniformity.</b></p>
Methods of application:	The prime coat should be applied with a flat brush; further coatings can also be sprayed and then reworked with a brush.
Cleaning your tools:	with turpentine substitute

---

Storage: cool, dry and frost-free. Re-seal opened packaging well and briefly turn upside down.

VOC-Value: EU threshold value for this product (Cat A/e):  
400 g/l VOC 2010).  
This product contains max. 400 g/l VOC.

---

**Identification Marking:** Please take note of our updated Safety Data Sheet available on the Internet at [www.jansen.de](http://www.jansen.de)

---

The technical information was compiled in accordance with the latest state of the art. An obligation for the general validity of the individual recommendations cannot, however, be accepted as the application and processing methods do not lie within our influence and the varying states of the substrates each require a decision as to the method of working suitable for workman and trade. The recommendations do not release the customer from the task of accepting responsibility for checking the products of the supplier company as to their suitability for the foreseen use. Applicable are the "General Terms and Conditions of Delivery and Payment in the Paint Industry" in the recommendation approved by the Federal Cartel Office (Bundeskartellamt) on 01. January 2018. On publication of this data sheet, all previous data sheets for this product become invalid.

UST-IdNr.: DE147923895